

## TECHINICAL SHEET

Description:	Thermal-acoustic insulation, in reel form	
Approval and monitoring:	ETA 17/0557	
Composition:	Cellulose (82-91%) NO ink, NO boron salts, NO glue	
Thermal conductivity:	$\lambda = 0,037 \text{ W/mK}$	(UNI EN 12667)
Permeability:	$\mu = 1,5$	(UNI EN 12086)
Fire Reaction:	B-s1, d0	(UNI EN 13501)
Mould growth:	0	(EN ISO 846)
Density:	18-25 kg/m <sup>3</sup>	
Dimensional stability	Excellent, the volume remains constant, if laid according to the technical requirements	